



M-8387 MP (Tank Plus)

Metatarsal Protection Work Boots

Upper : Full Grain Oily Cow Nubuck Leather +
TuffTarsal™ Protective Hard Cover

Lining : BactiVoid™ Beathable Sandwich Mesh

Insole : Anti-fatigue Memory Foam Insoles

Outsole : QuantumHold™ PU/Rubber Injection

Toecap : VortiGard™ Composite Toecap

Penetration : VortiGard™ Kevlar Midsole Plate

Size : EU 37-47#, UK 3-13#, US4-14#

CE EN ISO 20345:2022+A1:2024 S3S SR FO CI HI HRO MP

ASTM E 2149-2020 Approved Anti-microbial Lining & Insoles (Odor Resistant)

Application : Underground Mine, Open-Pit Mine, Crushing & Screening, Mineral Plant, Refinery Smelter etc



200 JOULE
TOECAP



SLIP-
RESISTANT



SHOCK
ABSORPTION



ANTI-STATIC



ANTI-NAIL
MIDSOLE



PETROL AND
CHEMICAL
RESISTANT



WATER
RESISTANT



OIL
RESISTANT



VortiGard™ Composite Toe Cap • EN ISO 20345:2022

Compoiste Toecap is light-weight and non-magnetic. The impact resistance can reach 200 joules from falling or rolling objects. The compression resistance can reach 15kN.



VortiGard™ Kevlar Plate Protection • EN ISO 20345:2022

Kevlar midsole plate is flexible and non-metallic. The penetration resistance can reach 1100 newtons from nail or other sharp objects. The flex resistance can reach to 1×10^6 flexion cycles without visable cracking.



LeathQua™ Cow Leather Upper • EN ISO 20345:2022

High quality full grain oily cow nubuck leather with thickness 1.6-1.8mm. It is treated with water resistant coating to protect feet from raining workday. The tear strength of upper leather can reach to 120 Newtons.




QuantumHold™ PU/Rubber Outsole • EN ISO 20345:2022

PU/Rubber outsoles are manufactured with Germany Fully Automatic Injection Technology. The midsole is 45 ± 5 degree hardness PU, which is soft and shock absorption. The outsole is natural rubber with 5%-10% nitrile, which is abrasion resistant, slip resistant, oil resistant and heat resistant.

Sole Bonding Strength Test

- EN ISO 20345:2022, 5.3 (Between Upper & Sole)
- Average Test Result 5.8 ± 5 (N/mm)



Upper, Lining & Bonding Strength Test Result

Leather Tear Strength $\geq$	120.0 Newtons
Leather Tensile Properties $\geq$	15.0 N/mm ²
Lining Tear Strength $\geq$	15.0 N/mm
Bonding Strength $\geq$	4.0 N/mm

✓ Protection With Slip Resistant (SR)	Result
Test Requirement : Forward Heel Slip ≥ 0.31 (Test methordL ISO 13287:2019) Backward Forepart Slip ≥ 0.36 (Test methordL ISO 13287:2019)	PASS
Standards : EN ISO20345:2022(5.3.5) , Test floor: Ceramic tile, Lubricant: Sodium lauryl sulphate	
✓ Protection With Metatarsal Device (MP)	Result
Test Requirement : Impact Energy $\geq 100 \pm 2$ Joules (More than 40mm after metatarsal impact test)	PASS
Standards : EN ISO 20345:2022(6.2.6.2).	
✓ Protection Resistant to Fuel Oil (FO)	Result
Test Requirement : Change in Volume and Change in Hardness (Outsole) is No More Than +12%(*)	PASS
Standards : EN ISO 20345:2022 (6.4.2)	
SAFETOE Standard Package Instruction (Average 42# for Reference)	
Shoes Weight : 1.3-1.4 KGS /Pair	Carton Weight : 14-15 KGS /Carton
1 Pair / Color Box , Dimensions : 32×24×12CM	10 Pair / Carton , Dimensions : 62×49×33CM



User Instructions:

- 1.) RECOMMENDED TO USE : Underground Mine, Open-Pit Mine, Crushing & Screening, Mineral Plant, Refinery Smelter etc.
- 2.) LIMITATION TO USE: It is very important that footwear selected must be suitable for the right workplaces. The protection against risks or hazards which are not mentioned in this document is not warranted.
- 3.) FITTING & SIZE: All footwear are marked with standard size on tongue label. Some are with different size comparison, such as EU size, UK size, US size etc. Please wear footwear in a suitable size.

Footwear which are too loose or too tight may not provide optimum level of protection.

- 4.) STORAGE: Keep the footwear in its original packaging, under ordinary temperature, non-humidity conditions and in clean, covered and ventilated premises.

- 5.) CLEANING: Clean footwear regularly by high quality cleaning treatments recommended as suitable for the purpose. Don't use caustic or corrosive cleaning agents.